



SPECIFICATION SHEET

PVC/Nitrile Foam

Property	-	Value
Density range	-	55-70kg/m ³
Temperature range	-	-50°C +116°C
Thermal conductivity (mean temp) BS874 part 2 1986 @+20	-	0.037W/(m.K)
Water vapour permeability Moisture resistance factor (BS4370 part 2 1973)	-	μ>5,000 0.13/μgm/N.h)
Water absorption (By volume after 28 days)	-	0.9% average
Fire performance BS76 part 7 1987 BS476 pat 6 1989	- -	Class "1" Class "O"
Noise reduction	-	Up to 30dB (A)
Resistance to oil and grease	-	Good
Colour	-	Black

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any particular application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable, but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied.