

RH Nuttall Limited

Great Brook Street
Nechells Green
Birmingham B7 4EN

Material Specification Sheet

e: sales@rhnutall.co.uk
t: 0121 359 2484
f: 0121 359 4439

RHN 18B



www.rhnutall.co.uk

Neoprene Bonded Cork

Property	Unit	Result
Binder	-	Neoprene Rubber
Cork Granule Size	mm	0.5/1
Colour	-	Natural
Density	-	0.75-0.9
Shore Hardness A	-	70-80
Compressibility @ 400psi	%	20-30
Recovery after	%	>80
Tensile strength		
Transversal direction	kg/cm	>15
Longitudinal direction	kg/cm	>15
Flexibility		
Original (F5)	-	-
ASTM No 1 Oil, 70h @100°C (F16)	-	-
Oven aged, 70h @ 100°C (F16)	-	-
Volume Change after Immersion		
ASTM No 1 Oil, 70h @ 100°C	%	-
ASTM No 3 Oil, 70h @ 100°C	%	-
ASTM Fuel A, 22h @ 23°C	%	-

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

