

**Material Specification
Sheet**e: sales@rhnutall.co.uk
t: 0121 359 2484
f: 0121 359 4439**RHN 18D**www.rhnutall.co.uk**Nitrile Bonded Cork**

Property	Unit	Result
Cork Granule Size	mm	2/3mm
Colour	-	Black
Binder	-	Cork/Nitrile
Density	-	0.6-0.7
Hardness Shore A	-	50-70
Compressibility 400psi	%	40-55
Recovery	%	75
Tensile Strength	kg/Cm	10.5
Flexibility		
Original F=5	-	No cracks
ASTM No 1 Oil, 70h @ 100°C (F16)	-	No cracks
Oven aged, 70h @ 100°C (F16)	-	No cracks
Volume change after Immersion		
ASTM No 1 Oil 70h @100°C	%	-10 to +10
ASTM No 3 Oil 70h @100°C	%	-5 to +40
ASTM Fuel A 22h @23°C	%	-5 to +10
Temperature Range	°C	-20 to 120

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

