

RH Nuttall Limited

Great Brook Street
Nechells Green
Birmingham B7 4EN

Material Specification Sheet

e: sales@rhnutall.co.uk
t: 0121 359 2484
f: 0121 359 4439

RHN 19B



www.rhnutall.co.uk

White Wool Felt – 40 Density

General Information

A firm industrial grade of felt that conforms to BS4060.

Tight manufacturing tolerances.

Good friction resistance.

Wide range of thicknesses.

This product is a natural wool fabric and therefore classes as a "clean, scoured wool blend", meaning because of the manufacturing process, it may contain other darker wool fibres as well as a percentage of non-wool material such as burrs and seeds.

Applications

Extreme sealing, anti-vibration, dust shielding, fluid storage, padding, sound deadening, oil and grease applications.

Thicknesses (1500mm wide)

3mm to 25mm

Property	Result
Fibre Composition	97% Minimum Wool
Density	0.44gm/cc
Standard Thickness Range	3mm-25mm
Colour	White
Operating Temperature	-62°C/+93°C
Tensile Strength	600 psi mm
Elongation at 100 psi	9
Coefficient of Noise Reduction (1") thick	0.41
BS Specification	Tolerances to BS.4060:2006
Ozone Resistance	Excellent

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

