

**Material Specification
Sheet**e: sales@rhnuttall.co.uk
t: 0121 359 2484
f: 0121 359 4439**RHN 15E**www.rhnuttall.co.uk**Closed Cell Polyethylene Foam – 25kg**

Description	Standard	Value	Unit
Density	ISO 845	25	Kg/m ³
Tensile Strength	ISO 1798	252	kPa
Elongation	ISO 1798	161	%
Compression 10%	ISO 844	34	kPa
Compression 25%	ISO 844	52	kPa
Compression 50%	ISO 844	113	kPa
Compression Set 0.5 Hrs	ISO 1856	16.0	%
Compression Set 24 Hrs	ISO 1856	4.0	%
Compression Set 50% 0.5 Hrs	ISO 1856	33.0	%
Compression Set 50% 24 Hrs	ISO 1856	21.0	%
Working Temperature Range	Internal	-60/+90	°C
Water Absorption % Vol (Max)	Internal	1	%
Water Vapour Transmission	ISO 1663	1.28	g/m ² *24 Hrs
Thermal Conductivity at 10c	ASTM C177	0.0380	W/mK
Thermal Conductivity at 40c	ASTM C177	0.0410	W/mK
Shore OO	ASTM D2240	46	OO
Flammability	FMVSS302	67	Mm/min
Dimensional Stability 24 Hrs at 70c <2%			

Please note - If holes were created during the foaming process, no more than six holes of 2mm diameter per 1000mm² sheet are acceptable.

Data represents typical values measured on a 10mm thick specimen and should be considered as guidelines only

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

