

RH Nuttall Limited

Great Brook Street
Nechells Green
Birmingham B7 4EN

Material Specification Sheet

e: sales@rhnutall.co.uk
t: 0121 359 2484
f: 0121 359 4439

RHN 2D



www.rhnutall.co.uk

White FQ EPDM Rubber

General Information

Excellent temperature range.

Excellent resistance to water, steam, ozone, ageing and many chemicals.

Not suitable for applications with petroleum liquids.

NB: Care should be taken in selecting the most suitable quality for each individual application. Advice is available but the final responsibility remains with the customer.

Thicknesses Available (10mx1.4m)

1mm to 6mm

Thicknesses Available (5mx1.4m)

8mm to 25mm

Thicknesses Available (1mx1m)

32mm; 38mm; 40mm

Property	Measure	Unit	Test
Elastomer	EPDM Rubber		
Colour	White		
Quality	EPDM Food Grade		
Hardness	60 $\pm$ 5	Shore Hardness A °	ISO 7619-1
S.G.	1.40	g/cm ²	ISO 2781
Tensile	6	N/mm ²	ISO 37
Elongation	500	%	ISO 37
Tear Strength	25	Kg/cm	ISO 34-1
Compression	38	%	ISO 37
Abrasion	200	mm ³	ISO 37
Operating Temperature	-40/+115	°c	
Roll Tolerances			
Width	$\pm$ 2%		ISO 3302 SW1
Length	$\pm$ 2%		ISO 3302 SW1
Thickness			
0.5mm-1mm	$\pm$ 0.2mm		
1.5mm-3mm	$\pm$ 0.3mm		
4mm-5mm	$\pm$ 0.4mm		
6mm	$\pm$ 0.5mm		
8mm	$\pm$ 0.7mm		
10mm-15mm	$\pm$ 1mm		
20mm	$\pm$ 1.4mm		
25mm	$\pm$ 1.75mm		

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

