

RH Nuttall Limited

Great Brook Street
Nechells Green
Birmingham B7 4EN

Material Specification Sheet

e: sales@rhnutall.co.uk
t: 0121 359 2484
f: 0121 359 4439

RHN 3E



www.rhnutall.co.uk

BS2752 C50 Neoprene Rubber

General Information

Good strength and suitability on minor mechanical applications.

Moderate resistant to weathering and oxidative ageing.

Resistant to some inorganic salts, ozone and acids.

Moderate resistance to petroleum-based products.

NB: Care should be taken in selecting the most suitable quality for each individual application. Advice is available but the final responsibility remains with the customer.

Thicknesses Available (10mx1.4m)

1mm to 6mm

Thicknesses Available (5mx1.4m)

8mm to 25mm

Thicknesses Available (1mx1m)

32mm; 38mm; 40mm

Property	Measure	Unit	Test
Elastomer	Neoprene		
Colour	Black		
Quality	BS2752-C50		
Hardness	50 ±5	Shore Hardness A °	ISO 7619-1
S.G.	1.37	g/cm ³	ISO 2781
Tensile	12	N/mm ²	ISO 37
Elongation	400	%	ISO 37
Compression Set	25	%	ISO 37
Operating Temperature	-30/+120	°C	
Roll Tolerances			
Width	±2%		ISO 3302 SW1
Length	±2%		
Thickness			
0.5mm-1mm	±0.2mm		
1.5mm-3mm	±0.3mm		
4mm-5mm	±0.4mm		
6mm	±0.5mm		
8mm	±0.7mm		
10mm-15mm	±1mm		
20mm	±1.4mm		
25mm	±1.75mm		

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

