

**Material Specification  
Sheet**e: sales@rhnutall.co.uk  
t: 0121 359 2484  
f: 0121 359 4439**RHN 26A**

www.rhnutall.co.uk

**Silicone Rubber (30SH)****General Information**

Excellent resistance to ozone, oxidation, UV, corona discharge, cosmic radiation, ionising radiation and weathering in general.

Excellent resistance to temperature extremes.

Sectors: Automotive, Domestic & Commercial, Catering, Construction, Electronics, Energy, Food & Beverage, HVAC, Lighting, Marine.**NB:** Care should be taken in selecting the most suitable quality for each individual application. Advice is available but the final responsibility remains with the customer.**Thicknesses Available (10mx1.2m)**

1mm to 20mm

**Colours Available – WRAS Approved for use with potable water at temperatures up to 85°C, number 1310541**

Translucent, Blue, White, Red, Black

**FDA Approved**

The colour range has been tested to, and is in accordance with, the American Food and Drugs Administration (FDA) 21 CFR 177-2600, BFR XV Empfehlung and colour bleed test according to BFR Empfehlung part B 11 &amp; Directive EC 1935/2004.

**Flammability Rating**

Meet the flammability requirements of FAR 25/JAR/JAR 25/CS 25 Appendix F, Part 1, (a)(1)(iv) and (a)(1)(v) horizontal flammability tests and Automotive Standard Part 571FMVSS302.

**General Characteristics**

| Test                  | Result                        | Standard       |
|-----------------------|-------------------------------|----------------|
| Brittle Point         | -80°C (-112°F)                | ASTM D746      |
| Limiting Oxygen Index | 24.0%                         | BS 2782 Part 1 |
| Thermal Conductivity  | 0.24 W.m-1 .K-1               |                |
| Radiation Resistance  | >105 Grays (107 Rads) typical |                |
| Dialectic Strength    | 23 kV.mm-1                    | VDE 0303       |
| Dielectric Constant   | 2.9                           | VDE 0303       |
| Dissipation Factor    | 3x10-4                        | VDE 0303       |
| Volume Resistivity    | 3x1015Ω.cm                    | VDE 0303       |
| Temperature           | -60°C+230°C intermittent      |                |

**Mechanical Properties**

| Property              | Unit       | Value      | Test Method                                           |
|-----------------------|------------|------------|-------------------------------------------------------|
| Hardness              | Shore A ±5 | 30         | ASTM D2240<br>DIN ISO 7619-1                          |
| Tensile Strength      | Mpa (Psi)  | 8.0 (1150) | ISO 37 Type 1<br>ASTM D412 die C<br>DIN 53504 type S1 |
| Elongation to Failure | %          | 500        | ISO 37 Type 1<br>ASTM D412 die C<br>DIN 53504 type S1 |
| Tear Strength         | N/mm       | 16.0       | ASTM D624 die B                                       |
| Compression Set       |            |            |                                                       |
| 24hrs @ 150°C         | %          | 23         | BS903 PT A6 type B DIN/ISO 815<br>type B              |
| 22hrs @ 300°C         | %          | 20         | ASTM D395 method B Type 2                             |

\*\*The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied\*\*

