

RH Nuttall Limited

Great Brook Street
Nechells Green
Birmingham B7 4EN

Material Specification Sheet

e: sales@rhnutall.co.uk
t: 0121 359 2484
f: 0121 359 4439

RHN 11E



www.rhnutall.co.uk

Grey Expanded Closed Cell EPDM Sponge

Property	Average Value
ASTM D1056 (2000)	2A2 C
Density (ASTM D3575)	150kg/m ³
Compression Set (23°C ± 2°C) 22HRS 25% Compression: measured after 24hrs (ASTM D1056)	5%
Shore Hardness "OO" Scales	40
Elongation- Minimum (ASTM D412)	>170%
Temperature Range (Constant)	-30°C/+90°C
Temperature Range (Intermittent)	+110°C
Water Absorption: Max Weight Change (ASTM D1056)	<2%
Tensile Strength (ASTM D412)	>500 kPa
Flame Resistance	FMVSS302
Environmental Protection	CFC & HCFC Free

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

