

RH Nuttall Limited

Great Brook Street
Nechells Green
Birmingham B7 4EN

Material Specification Sheet

e: sales@rhnuttall.co.uk
t: 0121 359 2484
f: 0121 359 4439

RHN 27E



www.rhnuttall.co.uk

Closed Cell Silicone Sponge – 27Lbs Density

Property	Test Method	Unit	Result
Density	BSENISO 845	kg.m ³	460
		Lb.ft ³	28.7
Hardness	ASTM D2240	Shore 00	70 +5
		Shore A	24
Compression Stress (40% Strain)	BSENISO 3386 Pt. 1.2	kPa	230
		psi	34
Tensile Strength	BSENISO 1798	MPa	1.5
		psi	217
Elongation to failure	BSENISO 1798	%	130
Compression Set 50% Compression 24 hrs recovery 22 hrs @70°C	BSENISO 1856	%	3.0
22 hrs @100°C	BSENISO 1856	%	4.3

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any application. All data relating to suitable uses and description information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The Company holds no legal or contractual responsibility for information supplied

